



Rope Characteristics

- Provide rotational stability to the lifted load
- Have less of a tendency to unlay when under load
- Designed for those applications where it is impractical to use a tag line, relocate the rope dead end, increase sheave sizes, eliminate odd-part reeving, and/or significantly reduce rope loading and rope fall length
- Must be carefully installed to prevent kinking or unlaying of the rope
- Should not be used with a permanent swivel
- Are easily damaged and therefore should not be shockloaded




8x19 Classification

- Recommended for hoisting unguided loads with a single part or multipart line
- Slightly stronger than 19x7
- Significantly more rugged than 19x7
- Resists drum crushing




19x7

- Recommended for hoisting unguided loads with a single part line
- Is more easily damaged than other spin-resistant ropes
- Spin-resistant characteristics are superior to that of the 8x19 Class



SFP 19™

- Recommended for both multipart load and single part fast line applications
- Offers EEIP breaking strength
- Provides fatigue resistance, abrasion resistance, and resistance to drum crushing
- Die drawn multistrand design increases flexibility




36DD™

- Recommended for applications where high strength, low rotation and ability to withstand long falls is needed
- Offers best operating and performance characteristics of all rotation-resistant ropes in terms of strength, fatigue and abrasion resistance, and rotational stability
- May be used with a swivel

Spin-resistant Wire Ropes

This chart compares the rotational properties of 8x19 Classification, 19x7, SFP 19 and 36DD wire ropes with a standard 6x25 IWRC. Note the superiority of the rotation-resistant ropes, particularly when the ropes are loaded to 50% of their breaking strengths.



ROPE DIAMETER		APPROX. WEIGHT (lb./ft.)				NOMINAL STRENGTH (tons)*			
inches	mm.	19x7	8x19 Class	SFP 19	36DD	19x7	8x19 Class	SFP 19	36DD
3/16	4.8	0.064	--	--	--	1.57	--	--	--
1/4	6.5	0.113	--	--	--	2.77	--	--	--
5/16	8.0	0.177	--	--	--	4.30	--	--	--
3/8	9.5	0.25	--	--	--	6.15	--	--	--
7/16	11.0	0.35	--	0.42	--	8.33	--	11.2	--
1/2	13.0	0.45	0.47	0.54	0.54	10.8	11.7	14.6	15.7
9/16	14.5	0.58	0.60	0.69	0.64	13.6	14.7	18.5	18.9
5/8	16.0	0.71	0.70	0.83	0.84	16.8	18.1	22.7	24.8
21/32	17.0	--	--	--	0.92	--	--	--	27.3
11/16	17.5	--	--	--	1.01	--	--	--	28.8
23/32	18.0	--	--	--	1.05	--	--	--	31.1
3/4	19.0	1.02	1.06	1.19	1.15	24.0	25.9	32.3	34.1
25/32	20.0	--	--	--	1.28	--	--	--	38.1
7/8	22.0	1.39	1.44	1.62	1.57	32.5	35.0	43.8	46.6
15/16	24.0	--	--	--	1.81	--	--	--	54.4
1	26.0	1.82	1.88	2.12	2.16	42.2	45.5	56.9	64.2
1-3/32	28.0	--	--	--	2.53	--	--	--	75.1
1-1/8	29.0	2.30	2.39	2.68	--	53.1	57.3	71.5	--
1-3/16	30.0	--	--	--	2.80	--	--	--	83.8
1-1/4	32.0	2.84	2.94	3.31	3.36	65.1	70.5	87.9	99.2
1-3/8	35.0	3.43	3.56	4.01	3.68	78.4	84.9	106.0	109.1
1-1/2	38.0	4.08	4.24	4.77	4.68	92.8	100.0	125.0	138.9

*Acceptance strength is not less than 2-1/2% below the nominal strengths listed. Tons of 2,000 lbs.



Williamsport Wire Rope Works, Inc.
 manufacturer of Bethlehem Wire Rope®

100 Maynard Street Post Office Box 3188
 Williamsport Pennsylvania 17701 USA
 telephone: 570-326-5146 facsimile: 570-327-4274
<http://www.williamsportrope.com>



Wire rope products will break if abused, misused or overused. Consult industry recommendations and OSHA Standards before using. Williamsport Wire Rope Works, Inc. warrants all Bethlehem Wire Rope® and Strand products. However, any warranty, expressed or implied as to quality, performance or fitness for use of wire rope products is always premised on the condition that the published breaking strengths apply only to new, unused rope, that the mechanical equipment on which such products are used is properly designed and maintained, that such products are properly stored, handled, used and maintained, and properly inspected on a regular basis during the period of use. Manufacturer shall not be liable for consequential or incidental damages or secondary charges including but not limited to personal injury, labor costs, a loss of profits resulting from the use of said products or from said products being incorporated in or becoming a component of any product. Williamsport Wire Rope Works, Inc. © 2000

Bethlehem Wire Rope®

