

## *PLASMA®* 12 STRAND

T3/T33 REV 011

Plasma<sup>®</sup> 12 strand is the highest strength synthetic rope available. *Plasma*<sup>®</sup> 12 strand is manufactured from Honeywell Spectra<sup>®</sup> Fiber that has been enhanced by Puget Sound Rope's patented recrystallization process. This process is especially effective in medium to large diameter ropes where strengths are over 50% higher and creep is significantly less than that of standard Spectra<sup>®</sup> 12 strand.

Plasma<sup>®</sup> 12 strand comes standard with a polyurethane finish and is easily spliced using a simple lockstitch type splice, 4-3-2 or 5-4-3 Tuck splice. Its soft, torque free braided construction provides easy handling.

- Highest strength
- Lowest stretch
- Low creep
- Soft hand
- Torque free
- Easy splicing
- Floats

**Type Approved Product** 






1012 SECOND STREET ANACORTES, WA 98221 USA TOLL FREE: 888-525-8488 TEL: 360-293-8488 FAX: 360-293-8480 www.thecortlandcompanies.com sales@psrope.com



	Nominal Diameter		Size	Approximate Weight		Minimum Tensile Strength	
	Inch	MM	Number (circ)	Lbs/100ft	Kq/100m	Pounds	kN
	.04	1	.12	.05	0.1	270	1.2
12 STRAND	.04	1.25	.12	.03	0.1	390	1.7
	.05	1.25	.13	.1	0.1	475	2.1
	.07	1.75	.21	.14	0.2	750	3.3
	.07	2.5	.3	.27	0.4	1,400	6.2
	1/8	3	3/8	.54	0.8	2,800	12.5
	3/16	5	9/16	1.12	1.7	5,500	24.5
	1/4	6	3/4	1.6	2.4	8,000	35.6
	5/16	8	15/16	2.5	3.7	11,700	52.0
	3/8	9	1-1/8	3.7	5.5	17,500	77.8
ABS AND DNV TYPE APPROVED SIZES							
12 STRAND	7/16	11	1-1/4	4.2	6.3	21,000	93.4
	1/2	12	1-1/2	6.4	9.5	31,300	139.2
	9/16	14	1-3/4	7.9	11.8	37,900	168.6
	5/8	16	2	10.6	15.8	51,400	228.6
	3/4	18	2-1/4	13.3	19.8	68,500	304.7
	13/16	20	2-1/2	15.9	23.7	74,000	329.2
	7/8	22	2-3/4	19.6	29.2	92,600	411.9
	1	24	3	23.4	34.8	110,000	489.3
	1-1/8	28	3-1/2	31.9	47.5	147,000	653.9
	1-1/4	30	3-3/4	36.2	53.9	165,000	734.0
	1-5/16	32	4	41.7	62.1	196,000	871.9
	1-1/2	36	4-1/2	51.7	76.9	221,000	983.1
	1-5/8	40	5	65.7	97.8	291,000	1294.4
	1-3/4	44	5-1/2	78.4	116.7	314,000	1396.7
STRAND	2	48	6	91.4	136	355,000	1579.1
A A	2-1/8	52	6-1/2	109	162.2	428,000	1903.8
Ĩ.	2-1/4	56	7	122	181.6	481,000	2139.6
5	2-1/2	60	7-1/2	148	220.2	530,000	2357.7
12 X 12	2-5/8	64	8	167	248.5	596,000	2651.1
N N	2-3/4	68	8-1/2	187	278.3	660,000	2935.8
-	3	72	9	214	318.5	780,000	3469.6
	3-1/8	76	9-1/2	235	349.7	850,000	3780.8
	3-1/4	80	10	261	388.4	940,000	4181.3
	3-5/8	88	11	324	482.2	1,250,000	5560.3
	4	96	12	394	586.4	1,520,000	6761.3

Tensile Strengths are determined in accordance with Cordage Institute 1500, Test Methods for Fiber Rope. Weights are calculated at linear density under standard preload (200d<sup>2</sup>) plus 4%. See reverse side for application and safety information.



Specific gravity	0.98*		
Welting point	284° F (140° C)*		
Critical temp.	150° F (65° C)*		
Coefficient of friction	0.09-0.12*		
Elongation at break	4%-5%		
Fiber water absorption	0%		
JV resistance	moderate		
Net abrasion	superior		
Dry abrasion	superior		

\* - value based on data supplied by the fiber manufacturer for new, dry fiber